

ABSTRACT OF THE DISCLOSURE

Amolding composition comprising (A) a fibrous material,  
(B) an inorganic filler, at least one of (C) a radical  
5 polymerizable unsaturated polyester having an acid value of  
3 to 60 KOHmg/g and (D) a radical polymerizable unsaturated  
polyester-polyamide having an acid value of 3 to 60 KOHmg/g,  
and (E) a radical generator, wherein component (B) has been  
internally added to at least one of component (C) and component  
10 (D) and a molding composition comprising (A) a fibrous material,  
at least one of (C) a radical polymerizable unsaturated polyester  
having an acid value of 3 to 60 KOHmg/g and (D) a radical  
polymerizable unsaturated polyester-polyamide having an acid  
value of 3 to 60 KOHmg/g, (E) a radical generator, and (F)  
15 a di- or higher valent metal salt of a fatty acid.

09901662.07101  
TOPP/0299T0660